



# **WARMUP YELLOW** 8A24.67

S3 SRC ESD

**PAG.** 1/2 **SIZES** 36 - 48



MATERIAL **MICROSUEDE** 

Soft, anti-stain material and very resistant to abrasion and tearing. Ideal for colder and wetter environments.

# TOE CAP ALUMINIUM REINFORCED

Lightweight toe cap against pressure up to 200 Joules. Rubber coating for extra protection and easy cleaning.

## TRACTION CONTROL REINFORCEMENT

Triple design that improves slip resistance.



## TOP GRIP REINFORCEMENT

Improved outsole's walking traction due to adapted angles and geometry in both extremities.



**TRIPLE SPEED** 

Smooth and extremely light midsole with a thin layer of ESD rubber. Oil resistancy and self-clean system.







FLOAT INSOLE





SHOE RESISTANCE TO

### **STANDARDS** EN ISO 20345:2011

**S3** - Closed heel area with the following characteristics:

**E** - Heel energy absorption

A - Antistatic footwear

FO - Resistance to fuel oil of the outsole

P - Penetration resistance sole

WRU - Water penetration resistant uppers

### ADITIONAL CHARACTERISTICS:

SRC - Slip resistance on ceramic + sodium lauryl sulfate and steel + glycerin

ESD - Electrostatic discharge (EN 61340-5-1)

### **ADVANTAGES**

Light | Comfortable | Breathable | Versatile | Sporty Look | Excellent anti-slip characteristics | Water absorption resistant materials

#### **WORK ENVIRONMENT**

Indoor Jobs | Courier | Administrative | Shopkeeper | Warehouse





**WARMUP YELLOW** 8A24.67

S3 SRC ESD

PAG. 2/2 CERTIFICATION NUMBER



### **TECHNICAL INFORMATION**

MATERIALS	STANDARDS	DESCRIPTION	UN.	RESULTS	EN ISO 20345 REQ.
<b>UPPER</b> - MICROSUEDE - Soft and anti-stain material, extremely abrasion and tearing resistant.	6.6+6.8	WATER VAPOUR PERMEABILITY COEFFICIENT OF PERMEABILITY	mg/cm <sup>2</sup> mg/cm <sup>2</sup>	2,5 22	min. 0,8 min. 15
	6.3 6.13	TEARING STRENGTH TRANSMITED WATER AFTER 60 MIN ABSORVED WATER 60 MIN	N 9 %	158 0,0 3,5	min. 60 max. 0,2 max. 30
<b>UPPER LINING</b> SPACE 3D - Special mesh fabric for excellent breathability. High durability of the material allows to keep the properties throughout the period of use.	6.6+6.8	COEFFICIENT OF PERMEABILITY	mg/cm <sup>2</sup>	25,3 202,4	min. 2,0 min. 20
	6.3	TEARING STRENG	N	41	min. 15
<b>HEEL LINING</b> SPACE 3D - Special mesh fabric for excellent breathability. High durability of the material allows to keep the properties throughout the period of use.	5.5.1 6.12	TEARING STRENGTH ABRASION RESISTANCE (DRY) ABRASION RESISTANCE (WET)	N - -	41 approved approved	min. 15 25.600 12.800
<b>ELECTROSTATIC DISCHARGE (ESD)</b> Conductive propert of the shoe.	es <b>61340-5-1</b>	ELECTRIC PROPERTIES ESD	ΜΩ	42	<100
INSOLE FLOAT - Non-metallic, extremely light and flexible.	6.2.1.1	PERFORATION RESISTANCE	Ν	approved	no perforation
<b>INSOCK</b> ACTIVE FOAM - Foam that helps to prevent muscle fatigue, while relieving heel pressure.	5.5.2 7.2	ABRASION RESISTANCE (DRY) ABRASION RESISTANCE (WET) WATER DESORPTION WATER ABSORPTION	cycles cycles % mg/cm2	- - - -	25.600 12.800 min 80 min 70
<b>SOLE</b> EVA & RUBBER - Specially created for the safety world. Includes anti-static with excellent abrasion and anti-slip proper	8.2 sies. 8.3 8.4 8.6	TEARING STRENGTH ABRASION RESISTANCE BENDING RESISTANCE OIL RESISTANCE VOLUME VARIATION OIL RESISTANCE INCREASED TOUGHNESS	N/mm mm³ mm % Shore A	9,2 110 0,4 - <10	min. 8 max. 150 max. 4 max 12 max 10
FULL SHOE	5.3.2.3 5.3.2.4 6.2.4 5.2	SLIP RESISTANCE ON CERAMIC FLOOR WITH WATER AND DETERGENT SLIP RESISTANCE ON STEEL FLOOR WITH GLYCERINE IMPACT RESISTANCE COMPRESSION RESISTANCE CHOCK ABSORPTION (HEEL) ADHESION STRENGTH SOLE/CUT	flat heel flat heel mm mm J N/mm	0,49 0,51 0,19 0,14 18,5 16,0 74	min. 0,32 min. 0,28 min. 0,18 min. 0,13 min. 15 min. 14 min. 20 min. 4,0

