

# SUPERSET BLACK 8A21.80

S1P SRC ESD

**PAG** 1/2 **SIZES** 36-48



## STANDARDS EN ISO 20345:2011

**S1P** - Closed heel area with the following characteristics:

- **E** Heel energy absorption
- A Antistatic footwear
- FO Resistance to fuel oil of the outsole
- P Penetration resistance sole

#### **ADITIONAL CHARACTERISTICS:**

**SRC** - Slip resistance on ceramic + sodium lauryl sulfate and steel + glycerin

ESD - Electrostatic discharge (EN 61340-5-1)

## **ADVANTAGES**

Light | Comfortable | Breathable | Versatile | Sporty Look | Excellent anti-slip characteristics

## **WORK ENVIRONMENT**

ESD ELECTROSTATIC DISCHARGE

Indoor Jobs | Courier | Administrative | Shopkeeper | Warehouse



SUPERSET BLACK 8A21.80

S1P SRC ESD

PAG 2/2 CERTIFICATION NUMBER



MATERIALS	STANDARDS	DESCRIPTION	UN.	RESULTS	EN ISO 20345 REQ.
<b>UPPER</b> - 3D AIR FLOW - 3D Mesh with extremely breathable and flexible characteristics.	6.6+6.8	WATER VAPOUR PERMEABILITY COEFFICIENT OF PERMEABILITY TEARING STRENGTH	mg/cm <sup>2</sup>	12	min. 0,8
	6.3		mg/cm <sup>2</sup>	456,4	min. 15
			N	188	min. 60
<b>UPPER LINING</b> SPACE 3D - Special mesh fabric for excellent breathability. High durability of the material allows to keep the properties throughout the period of use.	6.6+6.8	WATER VAPOUR PERMEABILITY	mg/cm <sup>2</sup>	25,3	min. 2,0
		COEFFICIENT OF PERMEABILITY TEARING STRENGTH	mg/cm <sup>2</sup>	202,4	min. 20
	6.3		Ν	41	min. 15
<b>HEEL LINING</b> SPACE 3D - Special mesh fabric for excellent breathability. High durability of the material allows to keep the properties throughout the period of use.	5.5.1	TEARING STRENGTH	N	41	min. 15
	6.12	ABRASION RESISTANCE (DRY) ABRASION RESISTANCE (WET)	-	approved approved	25.600 12.800
		,			12.000
<b>ELECTROSTATIC DISCHARGE (ESD)</b> Conductive propertie of the shoe.	61340-5-1	ELECTRIC PROPERTIES ESD	ΜΩ	42	<100
NSOLE FLOAT - Non-metallic, extremely light and flexible.	6.2.1.1	PERFORATION RESISTANCE	N	approved	no perforation
<b>INSOCK</b> ACTIVE FOAM - Foam that helps to prevent muscle fatigue, while relieving heel pressure.	5.5.2	ABRASION RESISTANCE (DRY)	cycles	-	25.600
	7.2	ABRASION RESISTANCE (WET) WATER DESORPTION	cycles %		12.800
	7.2	WATER ABSORPTION	mg/cm2	-	min 80 min 70
<b>SOLE</b> EVA & RUBBER - Specially created for the safety world. Includes anti-static with excellent abrasion and anti-slip propertie	8.2	ABRASION RESISTANCE (DRY)	N/mm	9,2	min. 8
	8.3 8.4	ABRASION RESISTANCE (WET) WATER DESORPTION	mm³ mm	110 0,4	max. 150 max. 4
	8.6	WATER ABSORPTION	%	-	max 12
			Shore A	<10	max 10
FULL SHOE	5.11	SLIP RESISTANCE ON CERAMIC FLOOR	flat	0.49	min. 0,32
	0.11	WITH WATER AND DETERGENT	heel	0,51	min. 0,28
		SLIP RESISTANCE ON STEEL FLOOR WITH GLYCERINE	flat heel	0,19 0,14	min. 0,18 min. 0.13
	5.3.2.3	IMPACT RESISTANCE	mm	18,5	min. 15
	5.3.2.4	COMPRESSION RESISTANCE	mm	16,0	min. 14
	6.2.4	CHOCK ABSORPTION (HEEL)	J	74	min. 20
	5.2	ADHESION STRENGTH SOLE/CUT	N/mm	7,3	min. 4,0

SHOE WEIGHT (SIZE 42): 520g



